

ROCKLANDS COPPER PROJECT (CDU 100%)

WILGAR UPDATE

**DIAMOND DRILLING DELIVERS FURTHER HIGH-GRADE
INTERSECTIONS OF GOLD AND SILVER
MINERALISATION INCLUDING;**

Diamond Drill Hole DODH294 intersects;

42m @ 4.30g/t AuEq

(from 0-42m)

Diamond Drill Hole DODH274 intersects;

36m @ 4.14g/t AuEq

(from 0-36m)

Diamond Drill Hole DODH268 intersects;

30m @ 4.32g/t AuEq

(from 1-31m)

Diamond Drill Hole DODH284 intersects;

30m @ 4.17g/t AuEq

(from 0-30m)

Diamond Drill Hole DODH310 intersects;

16m @ 11.7g/t AuEq

(from 2-18m)



Figure 1: Visible drysdallite (molybdenum mineral) in diamond drill hole DODH314 at approximately 27m, assay results for 27-28m 2.26% Mo, 5.28g/t Au, 400g/t Ag and 249ppm Te.

Diamond Drilling Delivers Further High-grade Gold and Silver Mineralisation

Further results from the vertical drilling programme at Wilgar have been received by the exploration team.

These holes are part of a series of short vertical holes, at varying distances across and along the interpreted strike direction of Wilgar mineralisation, that are currently being drilled to test below the extent of identified surface mineralisation.

Drilling is targeting potential repeats of the high-grade bonanza gold zone, whilst incrementally extending the mineralised footprint of the wider Wilgar polymetallic mineralised zone, which includes gold (Au), silver (Ag), tellurium (Te), molybdenum (Mo) and uranium (U).

Geological logging, hand-held XRF analysis, and initial assay results received to date in this programme, are confirming mineralisation extends from surface to at least 45m in places.

The latest results are shown on page 3 of this report.

Over 50 diamond holes are awaiting assays from the independent laboratory, significant results will be released as they come to hand.



Figure 2: Visible drysdallite (molybdenum mineral) in diamond drill hole DODH314, at approximately 28m - assay results for 27-28m 2.26% Mo, 5.28g/t Au, 400g/t Ag and 249ppm Te.

The Compensation Agreements with both the Landowner and Cloncurry Shire Council have been signed off.

Yours faithfully



Wayne McCrae
Chairman

DODH294	Width	AuEq	Au g/t	Ag g/t	Te ppm	U ppm	Mo ppm	From (m)	To (m)
Intersection 1	42m @	4.30	2.36	47.5	65.9	34.9	98.6	0m	- 42m
<i>including</i>	9m @	12.7	9.12	71.6	205	39.9	45.1	0m	- 9m

DODH274	Width	AuEq	Au g/t	Ag g/t	Te ppm	U ppm	Mo ppm	From (m)	To (m)
Intersection 1	36m @	4.14	2.02	50.7	65.0	86.9	59.1	0m	- 36m
<i>including</i>	8m @	8.17	4.13	89.4	171.3	45.4	236	11m	- 19m
<i>and</i>	5m @	6.96	3.41	78.4	45.3	405	6.80	29m	- 34m

DODH268	Width	AuEq	Au g/t	Ag g/t	Te ppm	U ppm	Mo ppm	From (m)	To (m)
Intersection 1	30m @	4.32	2.09	50.3	64.7	18.7	294	1m	- 31m
<i>including</i>	5m @	16.1	10.4	147	249	35.7	20.6	2m	- 7m

DODH284	Width	AuEq	Au g/t	Ag g/t	Te ppm	U ppm	Mo ppm	From (m)	To (m)
Intersection 1	30m @	4.08	1.78	61.1	73.4	38.5	61.0	0m	- 30m
<i>including</i>	15m @	7.47	3.40	110	138	40.0	94.4	0m	- 15m

DODH310	Width	AuEq	Au g/t	Ag g/t	Te ppm	U ppm	Mo ppm	From (m)	To (m)
Intersection 1	16m @	11.7	3.54	180	161	26.0	1590	2m	- 18m
<i>including</i>	3m @	50.2	14.8	733	673	88.8	8110	6m	- 9m

DODH276	Width	AuEq	Au g/t	Ag g/t	Te ppm	U ppm	Mo ppm	From (m)	To (m)
Intersection 1	26m @	2.60	0.40	28.1	21.9	435	4.92	0m	- 26m

DODH296	Width	AuEq	Au g/t	Ag g/t	Te ppm	U ppm	Mo ppm	From (m)	To (m)
Intersection 1	20m @	3.32	1.15	68.9	51.2	14.1	4.40	0m	- 20m
<i>including</i>	5m @	6.21	3.92	59.8	94.6	19.4	4.20	1m	- 6m

DODH303	Width	AuEq	Au g/t	Ag g/t	Te ppm	U ppm	Mo ppm	From (m)	To (m)
Intersection 1	26m @	3.47	0.71	81.9	79.8	26.6	9.81	0m	- 26m
<i>including</i>	10m @	5.65	1.34	119	155	29.4	15.1	6m	- 16m

DODH306	Width	AuEq	Au g/t	Ag g/t	Te ppm	U ppm	Mo ppm	From (m)	To (m)
Intersection 1	26m @	1.96	0.19	53.3	36.9	48.5	0	1m	- 27m

DODH314	Width	AuEq	Au g/t	Ag g/t	Te ppm	U ppm	Mo ppm	From (m)	To (m)
Intersection 1	15m @	0.60	0.13	16.8	4.12	4.63	3.40	0m	- 15m
Intersection 2	5m @	17.8	1.87	134	81.5	43.8	8280	25m	- 30m

cut-off grade of 0.4g/t AuEq with 3m allowance for internal waste

Competent Person Statement

The information in this report that relates to Exploration Results is based on information compiled by Mr Andrew Day. Mr Day is employed by GeoDay Pty Ltd, an entity engaged, by CuDeco Ltd to provide independent consulting services. Mr Day has a BAppSc (Hons) in geology and he is a Member of the Australasian Institute of Mining and Metallurgy (Member #303598). Mr Day has sufficient experience which is relevant to the style of mineralization and type of deposits under consideration and to the activity which he is undertaking to qualify as a Competent Person as defined in the 2004 Edition of the "Australasian Code for Reporting of Exploration Results, Mineral Resources and Ores Reserves". Mr Day consent to the inclusion in this report of the information in the form and context in which it appears.

The information in this report insofar as it relates to Metallurgical Test Results and Recoveries, is based on information compiled by Mr Peter Hutchison, MRACI Ch Chem, MAusIMM, a full-time executive director of CuDeco Ltd. Mr Hutchison has sufficient experience in hydrometallurgical and metallurgical techniques which is relevant to the results under consideration and to the activity which he is undertaking to qualify as a competent person for the purposes of this report. Mr Hutchison consents to the inclusion in this report of the information, in the form and context in which it appears.

Wilgar style mineralisation

Polymetallic and rare element hosting prospect, which includes mineralisation of Au, Mo, Ag, Te, Se, ±U. The high-grade gold, silver and tellurium may be present as tellurides and mineralisation may be related to an IRGS (Intrusion-Related Gold System).

Notes on Assay Results

All analyses are carried out at internationally recognized, independent, assay laboratories. Quality Assurance (QA) for the analyses is provided by continual analysis of known standards, blanks and duplicate samples as well as the internal QA procedures of the respective independent laboratories.

Wilgar drill intersections reported have been calculated on the basis of a gold cut-off grade of 0.4g/t AuEq with 3m allowance for internal waste.

Reported intersections are down-hole widths. Weighted averages are reported in drill holes with more than one intercept of mineralization.

Au = Gold
Ag = Silver
Te = Tellurium
Mo = Molybdenum
Pb = Lead
Cu = Copper
Co = Cobalt
U = Uranium
Se = Selenium
Zn = Zinc

Gold (Au) Equivalent Calculation

The formula is based on metal prices of:

Gold \$1200.00 USD/ounce

Silver \$30.00 USD/ounce

Tellurium \$300.00 USD/kg

U₃O₈ \$45.00 USD/lb

Molybdenum \$25.00 USD/lb

It the absence of metallurgical test work on this new style of mineralisation a recover or 100% has been used in the Gold Equivalent Calculations. AuEq results are calculated to 2 decimal places and reported in mineralised intercepts to 3 significant figures. Uranium results are converted to U₃O₈ for calculation purposes; Uranium ppm results are multiplied by a conversion factor of 1.1792 to account for the oxide form of the uranium compound.

Bedrock Drilling








Bedrock drilling at Rocklands is completed with the Company's own Ingersoll Rand, LM500C Rotary Air Blast (RAB), Hydraulic Crawler Drill, which drills vertical holes from the surface down until hard bedrock is reached. When reached, the drill continues for another metre before stopping. Samples are taken down hole in 1 metre intervals from surface, including the last metre which is typically hard bedrock. A six metre hole typically provides 5m of softer, decomposed surface material (colluvium, alluvium, regolith or just plain soil), and one metre (the last metre), of fresh bedrock. The depth of the softer cover material at Rocklands generally varies from 2 to 14 metres in thickness.

Hole Location Table:

Hole ID	Easting	Northing	RL (m)	Azi (°)	Dip (°)	Hole Depth (m)
DODH268	432288.2	7715678.6	237.3	000	-90	56.2
DODH274	432272.9	7715684.6	237.4	000	-90	50
DODH276	432269.4	7715686.9	237.6	000	-90	59.5
DODH284	432282.7	7715684.2	237.5	000	-90	50.5
DODH294	432283.7	7715678.6	237.3	000	-90	50.5
DODH296	432275.1	7715678.8	237.4	000	-90	53.5
DODH303	432269.4	7715682.3	237.6	000	-90	50
DODH306	432264.0	7715683.8	237.5	000	-90	50.5
DODH310	432293.1	7715681.8	237.1	000	-90	50.5
DODH314	432294.7	7715668.6	235.6	000	-90	35.5

Datum: AGD66 Project: UTM54 surveyed with Differential GPS (1 decimal place, 10cm accuracy) and/or handheld GPS (no decimal places, 4m accuracy).

Colour Ranges for Gold Equivalent (AuEq) values, used in the following Assay Results Tables;

AuEq	From	To
	0	<0.5
	0.5	<1
	1	<2
	2	<5
	5	<10
	10	<15
	15+	

Note: 1ppm = 1g/t

Assay Results Legend

- "nn"	Negatives values indicated result below lower detection limit ("nn"= lower detection limit)
LNR	Lab Not Receive (ie, sample not received at Assay Lab)
I/S	Insufficient Sample available to obtain result
DIP	sample Destroyed In Preparation
X	result below detection
-	sample not assayed

Hole ID	Depth Fm	Depth To	Au (ppm)	Ag (ppm)	Te (ppm)	U (ppm)	Mo (ppm)	AuEq (g/t)
DODH268	1	2	1.67	33.5	43.6	14.7	14	2.91
DODH268	2	3	4.59	129	74.6	13.1	13	8.45
DODH268	3	4	12.3	260	391	57.7	19	22.04
DODH268	4	5	11.4	250	333	30	33	20.38
DODH268	5	6	15.3	19.2	261	36.3	22	17.95
DODH268	6	7	8.34	76	184	41.6	16	11.82
DODH268	7	8	1.14	51.8	28.6	12.8	16	2.72
DODH268	8	9	0.85	41.7	22.6	14.3	214	2.42
DODH268	9	10	0.31	56.9	227	34.4	31	3.65
DODH268	10	11	1.12	15	38.7	39.2	1460	4.00
DODH268	11	12	0.08	0.7	3.7	16.5	101	0.32
DODH268	12	13	0.53	15.2	29.7	10.7	1130	2.79
DODH268	13	14	0.15	8.5	11.7	9.08	19	0.51
DODH268	14	15	0.17	71.4	10.8	4.78	20	2.08
DODH268	15	16	0.35	51.7	16.9	4.16	60	1.87
DODH268	16	17	0.32	44.6	26.4	17.3	64	1.78
DODH268	17	18	0.21	29.8	8.1	21	65	1.17
DODH268	18	19	0.14	46.8	6.4	12.3	32	1.44
DODH268	19	20	0.08	5.8	4	10.8	8	0.30
DODH268	20	21	0.09	8.8	6.1	16.3	31	0.45
DODH268	21	22	0.17	12.7	5.1	6.88	18	0.57
DODH268	22	23	0.08	14.2	5	5.37	-5	0.49
DODH268	23	24	0.39	46.8	30.5	6.04	8	1.83
DODH268	24	25	0.11	16.6	17.1	5.94	58	0.76
DODH268	25	26	0.46	33.3	32.3	17	413	2.19
DODH268	26	27	0.99	70.9	37.5	35.1	1190	4.86
DODH268	27	28	0.07	5.6	8.8	18.8	131	0.52
DODH268	28	29	0.54	40.9	48.1	23.6	2790	5.99
DODH268	29	30	0.54	46	26.7	13.6	702	2.94
DODH268	30	31	0.06	4.6	2.6	10.7	152	0.44
DODH268	31	32	0.03	2.6	1.4	9.05	56	0.21
DODH268	32	33	-0.01	0.5	0.4	4.91	23	0.06
DODH268	33	34	0.03	1.1	1.3	3.36	-5	0.08
DODH268	34	35	0.03	0.8	0.5	6.99	14	0.10
DODH268	35	36	0.01	0.8	0.5	5.56	6	0.06
DODH268	36	37	0.03	1.4	0.8	7.28	50	0.16
DODH268	37	38	-0.01	0.7	0.3	6.54	8	0.05
DODH268	38	39	-0.01	0.6	0.2	6.14	-5	0.04
DODH268	39	40	0.01	0.9	0.4	5.14	-5	0.05
DODH268	40	41	-0.01	1.2	0.5	3.45	-5	0.04
DODH268	41	42	0.02	1.5	0.5	3.69	-5	0.07
DODH268	42	43	0.01	-0.5	0.1	2.61	-5	0.02
DODH268	43	44	-0.01	-0.5	0.1	2.63	-5	0.01
DODH268	44	45	-0.01	-0.5	-0.1	3.34	-5	0.01
DODH268	45	46	0.01	-0.5	-0.1	3.42	-5	0.02
DODH268	46	47	-0.01	-0.5	-0.1	5.16	-5	0.02
DODH268	47	48	-0.01	-0.5	-0.1	4.47	-5	0.01
DODH268	48	49	0.01	-0.5	-0.1	4.23	-5	0.02
DODH268	49	50	-0.01	-0.5	-0.1	2.54	-5	0.01

Hole ID	Depth Fm	Depth To	Au (ppm)	Ag (ppm)	Te (ppm)	U (ppm)	Mo (ppm)	AuEq (g/t)
DODH274	0	1	0.15	24.3	10.5	17	10	0.90
DODH274	1	2	0.71	24.6	35.4	33.2	23	1.73
DODH274	2	3	0.13	20.1	16.4	35.1	9	0.88
DODH274	3	4	0.81	26.2	58.5	60.5	9	2.12
DODH274	4	5	2.88	52.9	79.7	49.1	6	4.98
DODH274	5	6	7.31	33.8	184	54.2	24	9.78
DODH274	6	7	0.11	41.5	36.1	33.4	6	1.54
DODH274	7	8	4.1	52	93.5	46.6	7	6.28
DODH274	8	9	0.51	32.6	13	13.2	9	1.48
DODH274	9	10	0.06	24.3	3.9	16.8	-5	0.75
DODH274	10	11	0.18	44.7	19	22.5	7	1.52
DODH274	11	12	5.04	94.4	269	77.1	85	9.85
DODH274	12	13	13	107	394	100	571	19.86
DODH274	13	14	2.01	89.9	194	34.6	803	7.02
DODH274	14	15	0.23	77.4	29.6	26.8	279	2.88
DODH274	15	16	1.22	172	140	37.8	49	6.79
DODH274	16	17	0.02	12.4	22.6	6.77	14	0.55
DODH274	17	18	1.28	142	139	43.4	39	6.10
DODH274	18	19	10.2	20.1	182	36.9	48	12.30
DODH274	19	20	0.11	32.9	5.9	34.3	23	1.12
DODH274	20	21	0.03	0.5	0.8	6.35	9	0.08
DODH274	21	22	0.06	4.1	2.8	18.6	36	0.29
DODH274	22	23	1.16	120	60.7	8.15	7	4.67
DODH274	23	24	1.43	72.3	58	18.8	6	3.75
DODH274	24	25	0.11	39.5	17.2	23.7	-5	1.30
DODH274	25	26	0.44	17.6	13	27.3	-5	1.06
DODH274	26	27	0.04	3	1.6	26.7	-5	0.21
DODH274	27	28	0.05	3.7	1.6	7.69	-5	0.18
DODH274	28	29	0.33	17.4	9.3	88.4	8	1.12
DODH274	29	30	3.4	101	37.5	39.9	12	6.35
DODH274	30	31	11.2	250	168	68.7	-5	18.96
DODH274	31	32	2.31	31.2	15.9	11	-5	3.25
DODH274	32	33	0.03	2.3	1.2	186	9	0.67
DODH274	33	34	0.1	7.6	4	1720	13	5.56
DODH274	34	35	0.5	7.8	6.5	89.8	-5	1.02
DODH274	35	36	1.43	23.6	16.3	7.2	6	2.18
DODH274	36	37	-0.01	-0.5	0.1	7.65	-5	0.02
DODH274	37	38	-0.01	-0.5	-0.1	9.48	-5	0.03
DODH274	38	39	0.01	0.9	0.6	17.1	18	0.11
DODH274	39	40	-0.01	-0.5	0.2	4.42	-5	0.01
DODH274	40	41	-0.01	-0.5	-0.1	3.98	-5	0.01
DODH274	41	42	-0.01	-0.5	0.2	5.25	-5	0.02
DODH274	42	43	0.02	1.2	0.7	5.25	-5	0.07
DODH274	43	44	0.02	1.3	1	4.86	-5	0.08
DODH274	44	45	-0.01	1.1	0.6	2.89	-5	0.04
DODH274	45	46	-0.01	3.1	1.4	3.23	-5	0.10
DODH274	46	47	-0.01	-0.5	0.3	3.43	-5	0.01
DODH274	47	48	-0.01	-0.5	-0.1	3.36	-5	0.01
DODH274	48	49	-0.01	5.5	1.2	7.89	-5	0.17
DODH274	49	50	0.02	1.5	0.6	5.3	-5	0.08

Hole ID	Depth Fm	Depth To	Au (ppm)	Ag (ppm)	Te (ppm)	U (ppm)	Mo (ppm)	AuEq (g/t)
DODH276	0	1	0.21	38.5	12.7	20.8	-5	1.33
DODH276	1	2	0.11	56.4	12.9	15.5	7	1.68
DODH276	2	3	0.06	43.2	4.3	30.8	-5	1.27
DODH276	3	4	2.02	36	169	52.8	8	4.41
DODH276	4	5	0.27	40.6	11.9	23.9	6	1.46
DODH276	5	6	0.09	21.7	3.1	15.5	-5	0.70
DODH276	6	7	0.09	37	6.7	58.8	-5	1.25
DODH276	7	8	1.95	25.4	34.1	36.8	-5	2.96
DODH276	8	9	0.21	26.9	8	17.1	8	1.01
DODH276	9	10	0.52	42.1	102	18.9	54	2.50
DODH276	10	11	0.47	56.6	61.6	25.5	32	2.49
DODH276	11	12	0.07	24	3.8	24.8	6	0.78
DODH276	12	13	0.05	10.2	2	18.8	7	0.39
DODH276	13	14	0.07	11	2.1	110	-5	0.69
DODH276	14	15	0.12	15.6	3.1	129	-5	0.93
DODH276	15	16	0.19	11.7	3.3	303	-5	1.43
DODH276	16	17	0.9	27.9	16.5	627	-5	3.63
DODH276	17	18	0.06	2.6	1.6	865	-5	2.76
DODH276	18	19	0.08	7.1	4.2	1230	-5	4.02
DODH276	19	20	0.64	27.7	16.1	808	-5	3.91
DODH276	20	21	0.15	2.7	2.3	1160	-5	3.75
DODH276	21	22	0.23	4.1	2.9	1970	-5	6.33
DODH276	22	23	0.16	2.5	1.7	1100	-5	3.57
DODH276	23	24	0.18	10	5.4	854	-5	3.06
DODH276	24	25	1.16	142	71.6	1580	-5	10.06
DODH276	25	26	0.44	8.2	5.8	223	-5	1.37
DODH276	26	27	0.03	-0.5	0.3	14.4	-5	0.08
DODH276	27	28	-0.01	-0.5	0.1	21	-5	0.06
DODH276	28	29	-0.01	-0.5	-0.1	9.68	-5	0.03
DODH276	29	30	0.01	0.8	0.6	19.4	-5	0.09
DODH276	30	31	-0.01	-0.5	-0.1	6.2	-5	0.02
DODH276	31	32	0.11	-0.5	-0.1	4.88	-5	0.12
DODH276	32	33	-0.01	-0.5	-0.1	5.82	-5	0.02
DODH276	33	34	-0.01	-0.5	-0.1	3.63	-5	0.01
DODH276	34	35	-0.01	-0.5	-0.1	4.46	-5	0.01
DODH276	35	36	-0.01	-0.5	-0.1	9.09	-5	0.03
DODH276	36	37	0.02	-0.5	0.2	5.18	-5	0.04
DODH276	37	38	-0.01	-0.5	-0.1	4.16	-5	0.01
DODH276	38	39	-0.01	-0.5	-0.1	3.94	-5	0.01
DODH276	39	40	-0.01	-0.5	-0.1	2.43	-5	0.01
DODH276	40	41	-0.01	-0.5	-0.1	3.6	-5	0.01
DODH276	41	42	-0.01	-0.5	-0.1	3.57	-5	0.01
DODH276	42	43	-0.01	-0.5	-0.1	3.52	-5	0.01
DODH276	43	44	-0.01	-0.5	-0.1	6.06	-5	0.02
DODH276	44	45	-0.01	-0.5	-0.1	4.81	-5	0.01
DODH276	45	46	-0.01	-0.5	-0.1	2.7	-5	0.01
DODH276	46	47	-0.01	-0.5	-0.1	2.65	-5	0.01
DODH276	47	48	-0.01	-0.5	-0.1	2.63	-5	0.01
DODH276	48	49	-0.01	-0.5	-0.1	3.62	-5	0.01
DODH276	49	50	-0.01	-0.5	-0.1	3.32	-5	0.01

Hole ID	Depth Fm	Depth To	Au (ppm)	Ag (ppm)	Te (ppm)	U (ppm)	Mo (ppm)	AuEq (g/t)
DODH284	0	1	5.9	98.3	160	85.1	6	9.87
DODH284	1	2	16.9	123	451	44.4	15	23.64
DODH284	2	3	2.79	111	135	81.3	11	6.88
DODH284	3	4	0.68	32.2	19.6	15.8	9	1.70
DODH284	4	5	3.03	59.2	112	38.7	63	5.59
DODH284	5	6	1.6	43.3	46.7	30.9	63	3.23
DODH284	6	7	0.48	43.9	8.8	13.1	115	1.85
DODH284	7	8	1.22	58.9	27.8	20.5	131	3.16
DODH284	8	9	4.28	80.3	110	29.8	702	8.24
DODH284	9	10	3.43	153	177	41.7	83	8.88
DODH284	10	11	2.64	115	191	42.3	78	7.24
DODH284	11	12	0.4	63.2	13.1	18.1	16	2.16
DODH284	12	13	0.23	82.3	14.2	17	13	2.47
DODH284	13	14	4.55	360	397	72	88	16.98
DODH284	14	15	2.84	220	206	49.4	23	10.12
DODH284	15	16	0.04	5.7	3.2	20.7	11	0.29
DODH284	16	17	0.17	9.1	9.3	14.2	15	0.53
DODH284	17	18	0.22	18	37	11.8	20	1.02
DODH284	18	19	0.39	5.1	17.4	21	88	0.84
DODH284	19	20	0.1	2.3	3.1	5.04	180	0.45
DODH284	20	21	0.05	10.3	3.8	58.9	14	0.54
DODH284	21	22	0.03	4	0.9	22.7	-5	0.21
DODH284	22	23	0.71	28.3	17.4	14.1	-5	1.60
DODH284	23	24	0.18	38.6	9.6	156	10	1.71
DODH284	24	25	0.08	13.7	5.1	43.3	-5	0.59
DODH284	25	26	0.11	9.6	5.2	79.9	18	0.66
DODH284	26	27	0.11	11.7	7	28.1	59	0.63
DODH284	27	28	0.15	12.5	5.9	25.2	-5	0.58
DODH284	28	29	0.05	7.1	2.8	23.5	-5	0.32
DODH284	29	30	0.07	13.3	5.6	30	-5	0.54
DODH284	30	31	0.01	2.3	1.1	8.16	-5	0.10
DODH284	31	32	0.06	1	1.1	7.76	-5	0.12
DODH284	32	33	-0.01	-0.01	-0.1	2.98	-5	0.01
DODH284	33	34	-0.01	-0.01	-0.1	4.41	-5	0.01
DODH284	34	35	-0.01	0.7	0.1	3.86	-5	0.03
DODH284	35	36	-0.01	-0.01	-0.1	2.75	-5	0.01
DODH284	36	37	-0.01	-0.01	-0.1	2.96	-5	0.01
DODH284	37	38	-0.01	-0.01	-0.1	2.95	-5	0.01
DODH284	38	39	0.01	1	0.5	3.56	-5	0.05
DODH284	39	40	0.04	5.9	4.8	7.9	-5	0.25
DODH284	40	41	0.01	2.5	1.1	6.2	-5	0.10
DODH284	41	42	0.04	5.6	2	15.1	-5	0.24
DODH284	42	43	0.11	12.9	7.5	10.6	-5	0.52
DODH284	43	44	0.02	4.7	1.7	4.48	-5	0.16
DODH284	44	45	0.15	12.6	13.4	12.2	-5	0.61
DODH284	45	46	0.01	1.1	0.5	3.63	-5	0.05
DODH284	46	47	-0.01	0.6	0.2	3.12	-5	0.03
DODH284	47	48	-0.01	-0.01	0.4	3.51	-5	0.01
DODH284	48	49	-0.01	0.6	0.1	2.88	-5	0.02
DODH284	49	50	-0.01	-0.01	-0.1	2.78	-5	0.01

Hole ID	Depth Fm	Depth To	Au (ppm)	Ag (ppm)	Te (ppm)	U (ppm)	Mo (ppm)	AuEq (g/t)
DODH294	0	1	4.91	37	97.2	26.3	13	6.69
DODH294	1	2	15.4	56.7	313	46.6	19	19.42
DODH294	2	3	15	66.3	450	31.1	17	20.28
DODH294	3	4	4.36	51.8	92.3	37.3	26	6.52
DODH294	4	5	15.9	91.6	235	54.8	25	20.22
DODH294	5	6	12.9	70.7	177	39.1	61	16.25
DODH294	6	7	0.84	51.8	35.2	31.1	41	2.56
DODH294	7	8	3.13	65.6	140	55.6	154	6.25
DODH294	8	9	9.67	153	306	36.8	50	16.06
DODH294	9	10	1.01	63.3	34	7.22	9	2.89
DODH294	10	11	0.7	57.7	32.4	27.3	13	2.50
DODH294	11	12	1.01	36.1	28.5	42	52	2.34
DODH294	12	13	0.17	27.7	6.2	7.01	15	0.95
DODH294	13	14	0.14	46.7	7.4	5.51	5	1.39
DODH294	14	15	0.99	117	58.8	12.9	309	4.85
DODH294	15	16	0.24	27.6	11.7	6.88	11	1.06
DODH294	16	17	0.13	56.3	40.7	24.3	12	1.94
DODH294	17	18	1.87	40.1	43.7	32.2	15	3.33
DODH294	18	19	0.25	37	9.9	11.2	8	1.30
DODH294	19	20	3.88	63.8	151	22.1	11	6.73
DODH294	20	21	0.08	24.3	5.3	11.2	-5	0.76
DODH294	21	22	0.36	35.5	19.5	71.3	5	1.62
DODH294	22	23	0.15	17.7	10.8	166	26	1.22
DODH294	23	24	0.24	26.8	16.1	19.6	252	1.45
DODH294	24	25	0.02	2	0.8	15.1	15	0.14
DODH294	25	26	0.4	67.2	42	113	748	3.82
DODH294	26	27	0.12	10.7	6.6	15.5	119	0.66
DODH294	27	28	0.32	23.8	24.2	12.4	120	1.31
DODH294	28	29	0.08	2.7	4.3	16.6	30	0.27
DODH294	29	30	0.08	2.3	4.3	6.56	6	0.20
DODH294	30	31	2.25	230	202	108	307	10.34
DODH294	31	32	1.34	158	89.5	131	950	7.74
DODH294	32	33	0.11	9.5	4.7	82.1	206	0.93
DODH294	33	34	0.11	11.2	4.3	16.8	173	0.72
DODH294	34	35	0.2	16.8	8.8	63.7	178	1.14
DODH294	35	36	0.09	8.2	4.2	15.2	36	0.43
DODH294	36	37	0.03	2.4	1.4	10.4	22	0.16
DODH294	37	38	0.02	27.9	10.2	10	73	0.93
DODH294	38	39	0.29	55.3	23.8	6.94	10	1.89
DODH294	39	40	0.11	25.9	7	5.77	-5	0.83
DODH294	40	41	0.08	7.1	1.7	4.46	-5	0.28
DODH294	41	42	0.03	12.3	6.3	6.67	-5	0.41
DODH294	42	43	0.03	2.6	1.2	4.45	-5	0.12
DODH294	43	44	-0.01	0.9	0.5	3.3	-5	0.04
DODH294	44	45	-0.01	1.1	0.4	3.2	-5	0.04
DODH294	45	46	-0.01	1.1	-0.1	2.49	-5	0.04
DODH294	46	47	-0.01	0.8	-0.1	3.31	-5	0.03
DODH294	47	48	-0.01	-0.5	0.1	2.34	-5	0.01
DODH294	48	49	-0.01	2.3	0.6	3.17	-5	0.07
DODH294	49	50	-0.01	3.3	1	3.36	6	0.11

Hole ID	Depth Fm	Depth To	Au (ppm)	Ag (ppm)	Te (ppm)	U (ppm)	Mo (ppm)	AuEq (g/t)
DODH296	0	1	0.84	69	69.6	12	6	3.15
DODH296	1	2	4.82	57.9	89.2	14	9	7.02
DODH296	2	3	2.69	53.8	128	24.6	7	5.11
DODH296	3	4	1.08	31.7	82.7	15.6	-5	2.56
DODH296	4	5	2.21	34.4	71.3	8.08	-5	3.65
DODH296	5	6	8.78	121	102	34.8	5	12.71
DODH296	6	7	0.9	102	68.2	24.4	-5	4.05
DODH296	7	8	0.17	55.4	57.3	6.1	-5	2.02
DODH296	8	9	0.42	78.1	49.8	8.18	-5	2.78
DODH296	9	10	0.29	82.5	94.5	8.82	-5	3.11
DODH296	10	11	0.3	152	45.4	8.61	5	4.49
DODH296	11	12	0.09	86.7	26.8	10.7	7	2.51
DODH296	12	13	0.07	71.9	7.1	6.13	11	1.96
DODH296	13	14	0.06	56.5	4.8	7.9	12	1.55
DODH296	14	15	0.24	74.5	38.7	32	12	2.52
DODH296	15	16	0.05	89.3	27.4	28.9	9	2.60
DODH296	16	17	0.04	59.3	27.2	14.6	5	1.79
DODH296	17	18	0.02	56.3	29.7	8.08	-5	1.68
DODH296	18	19	-0.01	20.8	2.5	4.1	-5	0.55
DODH296	19	20	-0.01	24.2	1.5	3.98	-5	0.63
DODH296	20	21	-0.01	12.9	1.1	2.56	-5	0.34
DODH296	21	22	-0.01	9.4	0.8	10.9	-5	0.27
DODH296	22	23	0.01	-0.5	0.6	7.89	-5	0.04
DODH296	23	24	-0.01	-0.5	0.5	7.42	-5	0.03
DODH296	24	25	-0.01	-0.5	0.2	5.19	-5	0.02
DODH296	25	26	0.01	-0.5	0.2	2.22	-5	0.02
DODH296	26	27	0.01	-0.5	0.2	3.07	-5	0.02
DODH296	27	28	-0.01	-0.5	0.4	9.59	-5	0.03
DODH296	28	29	-0.01	0.5	0.1	22.9	-5	0.08
DODH296	29	30	-0.01	-0.5	0.1	4.35	-5	0.01
DODH296	30	31	-0.01	1	0.3	3.89	-5	0.04
DODH296	31	32	-0.01	-0.5	0.1	3.62	-5	0.01
DODH296	32	33	-0.01	-0.5	0.2	3.77	-5	0.01
DODH296	33	34	-0.01	-0.5	0.2	3.79	-5	0.01
DODH296	34	35	-0.01	-0.5	0.2	5	-5	0.02
DODH296	35	36	-0.01	0.8	-0.1	3.43	-5	0.03
DODH296	36	37	-0.01	-0.5	0.2	4.64	-5	0.02
DODH296	37	38	-0.01	-0.5	0.2	6.04	-5	0.02
DODH296	38	39	-0.01	-0.5	-0.1	6.1	-5	0.02
DODH296	39	40	-0.01	-0.5	0.4	4.95	-5	0.02
DODH296	40	41	-0.01	-0.5	0.1	5.08	-5	0.02
DODH296	41	42	-0.01	-0.5	-0.1	4.68	-5	0.01
DODH296	42	43	0.02	-0.5	0.2	3.88	-5	0.03
DODH296	43	44	0.02	3.2	0.1	4.7	-5	0.12
DODH296	44	45	0.03	-0.5	0.3	4.49	-5	0.05
DODH296	45	46	0.03	7.1	0.3	2.88	-5	0.22
DODH296	46	47	0.02	-0.5	0.2	2.24	-5	0.03
DODH296	47	48	0.02	-0.5	0.4	2.74	-5	0.03
DODH296	48	49	0.02	-0.5	0.2	3.47	-5	0.03
DODH296	49	50	0.02	-0.5	0.1	3	-5	0.03

Hole ID	Depth Fm	Depth To	Au (ppm)	Ag (ppm)	Te (ppm)	U (ppm)	Mo (ppm)	AuEq (g/t)
DODH303	0	1	0.62	15.8	27.6	17.1	17	1.31
DODH303	1	2	0.32	13.7	15.1	35.9	23	0.92
DODH303	2	3	0.12	16.7	10.9	28.8	17	0.73
DODH303	3	4	0.49	39.9	53	55.6	19	2.10
DODH303	4	5	0.78	111	85.7	104	10	4.55
DODH303	5	6	0.65	109	87.8	46.1	18	4.22
DODH303	6	7	3.75	250	374	81.1	23	13.19
DODH303	7	8	2.05	177	267	45.6	25	8.73
DODH303	8	9	3.04	76.1	472	59.5	28	8.83
DODH303	9	10	0.07	115	52.8	23.2	10	3.44
DODH303	10	11	0.1	98.5	51.4	22.7	9	3.04
DODH303	11	12	0.33	72.2	46.1	15.5	8	2.55
DODH303	12	13	0.59	53.6	28	11.8	17	2.21
DODH303	13	14	0.16	73.8	5.7	11.4	14	2.10
DODH303	14	15	0.6	181	91.1	8.34	8	5.87
DODH303	15	16	2.73	97.5	165	14.4	9	6.51
DODH303	16	17	0.29	84.7	13.1	6.65	-5	2.53
DODH303	17	18	0.14	48.9	12.1	4.16	-5	1.47
DODH303	18	19	0.1	71.7	12.9	4.65	-5	2.01
DODH303	19	20	1.26	48.7	139	54.5	-5	3.72
DODH303	20	21	0.14	50.3	29.1	10	-5	1.65
DODH303	21	22	0.04	83.8	16.5	5.41	-5	2.28
DODH303	22	23	0.02	90	5.5	11.2	-5	2.35
DODH303	23	24	0.01	80.2	11.5	5.89	-5	2.12
DODH303	24	25	0.01	47.5	1.6	3.74	-5	1.22
DODH303	25	26	-0.01	23	1.1	4.54	-5	0.60
DODH303	26	27	-0.01	1	0.2	3.38	-5	0.04
DODH303	27	28	-0.01	-0.5	0.3	2.99	-5	0.01
DODH303	28	29	-0.01	-0.5	0.2	4.49	-5	0.02
DODH303	29	30	-0.01	-0.5	0.1	7.89	-5	0.02
DODH303	30	31	-0.01	-0.5	0.1	6.81	-5	0.02
DODH303	31	32	-0.01	-0.5	0.2	9.76	-5	0.03
DODH303	32	33	0.03	-0.5	0.2	8.39	-5	0.06
DODH303	33	34	-0.01	-0.5	0.1	3.85	19	0.04
DODH303	34	35	0.01	-0.5	0.1	7.28	-5	0.03
DODH303	35	36	-0.01	-0.5	0.2	4.77	-5	0.02
DODH303	36	37	-0.01	-0.5	0.1	3.68	-5	0.01
DODH303	37	38	-0.01	-0.5	0.2	4.31	-5	0.01
DODH303	38	39	-0.01	-0.5	-0.1	3.91	-5	0.01
DODH303	39	40	-0.01	-0.5	-0.1	4.59	-5	0.01
DODH303	40	41	-0.01	-0.5	0.3	5.65	-5	0.02
DODH303	41	42	-0.01	-0.5	0.1	4.24	-5	0.01
DODH303	42	43	-0.01	-0.5	-0.1	3.71	-5	0.01
DODH303	43	44	-0.01	-0.5	0.2	4.68	-5	0.02
DODH303	44	45	-0.01	-0.5	-0.1	4.2	-5	0.01
DODH303	45	46	-0.01	-0.5	0.2	4.61	-5	0.02
DODH303	46	47	-0.01	-0.5	0.2	3.1	-5	0.01
DODH303	47	48	-0.01	-0.5	0.2	2.72	-5	0.01
DODH303	48	49	-0.01	-0.5	0.2	3.05	-5	0.01
DODH303	49	50	-0.01	-0.5	0.2	3.36	-5	0.01

Hole ID	Depth Fm	Depth To	Au (ppm)	Ag (ppm)	Te (ppm)	U (ppm)	Mo (ppm)	AuEq (g/t)
DODH306	0	1	0.11	7.7	6.3	6.46	-5	0.37
DODH306	1	2	0.08	17.4	10.5	13.4	-5	0.64
DODH306	2	3	0.77	96.7	166	154	-5	4.95
DODH306	3	4	0.29	63.1	46.8	178	-5	2.77
DODH306	4	5	0.44	88.8	40.5	75.2	-5	3.20
DODH306	5	6	1.12	141	142	226	-5	6.43
DODH306	6	7	0.15	76.4	39.6	96.5	-5	2.66
DODH306	7	8	0.09	37.6	7.9	16.3	-5	1.14
DODH306	8	9	0.21	39.6	25.1	36.1	-5	1.50
DODH306	9	10	0.81	45.8	49.7	37.4	-5	2.45
DODH306	10	11	0.07	56.6	25.3	32.6	-5	1.78
DODH306	11	12	0.15	28.3	14.9	46.4	-5	1.11
DODH306	12	13	0.23	42.1	23.2	99.6	-5	1.76
DODH306	13	14	0.14	22.4	12	63.3	-5	0.99
DODH306	14	15	0.04	26.8	3.9	79.4	-5	0.98
DODH306	15	16	0.06	39.2	14	25.3	-5	1.23
DODH306	16	17	0.02	43.4	15.1	7.62	-5	1.25
DODH306	17	18	0.04	40.4	35.7	5.29	-5	1.34
DODH306	18	19	0.11	88.5	87	10.5	-5	3.03
DODH306	19	20	0.11	112	92.6	15	-5	3.68
DODH306	20	21	0.04	83.2	38.3	12.9	-5	2.46
DODH306	21	22	0.02	38.8	19.1	6.25	-5	1.16
DODH306	22	23	0.05	19.8	10.1	4.14	-5	0.64
DODH306	23	24	0.03	46.3	18.4	7.93	-5	1.35
DODH306	24	25	0.01	28.6	14.4	5.4	-5	0.85
DODH306	25	26	-0.01	30	7	3.48	-5	0.81
DODH306	26	27	-0.01	31.8	0.3	2.58	-5	0.81
DODH306	27	28	-0.01	6.4	0.6	2.89	-5	0.17
DODH306	28	29	-0.01	2	0.3	3.43	-5	0.06
DODH306	29	30	-0.01	2	0.2	2.67	-5	0.06
DODH306	30	31	-0.01	-0.5	0.2	2.37	-5	0.01
DODH306	31	32	-0.01	-0.5	0.2	3.9	-5	0.01
DODH306	32	33	0.01	-0.5	0.3	7.87	-5	0.04
DODH306	33	34	-0.01	-0.5	0.2	4.98	-5	0.02
DODH306	34	35	0.01	-0.5	0.2	4.52	-5	0.03
DODH306	35	36	-0.01	-0.5	0.1	6.62	-5	0.02
DODH306	36	37	-0.01	-0.5	0.1	7.05	-5	0.02
DODH306	37	38	-0.01	-0.5	-0.1	5.44	-5	0.02
DODH306	38	39	-0.01	-0.5	0.1	3.03	-5	0.01
DODH306	39	40	-0.01	-0.5	0.1	2.85	-5	0.01
DODH306	40	41	-0.01	-0.5	0.1	2.72	-5	0.01
DODH306	41	42	-0.01	-0.5	0.2	2.71	-5	0.01
DODH306	42	43	-0.01	-0.5	0.1	8.34	13	0.04
DODH306	43	44	-0.01	-0.5	0.2	13.3	-5	0.04
DODH306	44	45	-0.01	-0.5	0.1	3.87	-5	0.01
DODH306	45	46	-0.01	-0.5	0.3	4.13	-5	0.01
DODH306	46	47	-0.01	-0.5	-0.1	3.15	-5	0.01
DODH306	47	48	-0.01	-0.5	0.2	4.02	-5	0.01
DODH306	48	49	-0.01	-0.5	0.2	3.25	-5	0.01
DODH306	49	50	0.02	-0.5	0.2	3.37	-5	0.03

Hole ID	Depth Fm	Depth To	Au (ppm)	Ag (ppm)	Te (ppm)	U (ppm)	Mo (ppm)	AuEq (g/t)
DODH310	0	1	0.16	4.6	4.8	5.23	-5	0.33
DODH310	1	2	0.14	5.5	3.7	5.55	-5	0.32
DODH310	2	3	1.13	41.4	51.1	12.7	11	2.62
DODH310	3	4	2.18	88.4	146	13.3	12	5.58
DODH310	4	5	3.51	46.8	89.6	12.8	24	5.45
DODH310	5	6	0.45	87.2	26.2	20.9	45	2.96
DODH310	6	7	5.77	200	285	39.2	2050	16.03
DODH310	7	8	31.8	1600	1460	182	19200	111.13
DODH310	8	9	6.87	400	275	45.3	3080	23.55
DODH310	9	10	1.9	135	138	16.5	186	6.66
DODH310	10	11	1.35	77.4	50	9.71	31	3.75
DODH310	11	12	0.89	59.3	28.4	8.59	21	2.65
DODH310	12	13	0.2	36.5	10.8	5.34	30	1.26
DODH310	13	14	0.19	47.8	9.7	18.7	462	2.18
DODH310	14	15	0.17	24.8	5.8	11.1	248	1.22
DODH310	15	16	0.01	3.8	0.6	3.47	6	0.13
DODH310	16	17	0.11	14.3	2	8.36	89	0.64
DODH310	17	18	0.03	23.1	1	7.78	9	0.65
DODH310	18	19	0.02	2.4	0.8	9.12	7	0.12
DODH310	19	20	0.02	2.4	1.1	7.04	-5	0.11
DODH310	20	21	0.02	0.8	0.4	4.46	5	0.06
DODH310	21	22	-0.01	-0.5	0.1	4.79	-5	0.02
DODH310	22	23	0.01	-0.5	0.4	6.37	-5	0.03
DODH310	23	24	-0.01	-0.5	0.4	5.43	-5	0.02
DODH310	24	25	-0.01	-0.5	0.2	4.31	6	0.02
DODH310	25	26	0.02	-0.5	0.4	6.12	9	0.05
DODH310	26	27	0.01	-0.5	0.5	5.23	9	0.04
DODH310	27	28	0.06	3	2.3	5.09	6	0.18
DODH310	28	29	-0.01	-0.5	-0.1	4.76	-5	0.01
DODH310	29	30	-0.01	-0.5	0.1	3.54	-5	0.01
DODH310	30	31	-0.01	-0.5	0.2	5.67	-5	0.02
DODH310	31	32	-0.01	-0.5	-0.1	4.2	-5	0.01
DODH310	32	33	-0.01	-0.5	-0.1	3.25	-5	0.01
DODH310	33	34	-0.01	-0.5	-0.1	4.12	-5	0.01
DODH310	34	35	-0.01	-0.5	-0.1	6.46	-5	0.02
DODH310	35	36	-0.01	-0.5	-0.1	7.41	-5	0.02
DODH310	36	37	-0.01	-0.5	-0.1	4.89	-5	0.01
DODH310	37	38	-0.01	-0.5	-0.1	3.79	-5	0.01
DODH310	38	39	-0.01	2.5	0.2	4.37	-5	0.08
DODH310	39	40	-0.01	-0.5	-0.1	3.36	-5	0.01
DODH310	40	41	-0.01	-0.5	0.1	2.96	-5	0.01
DODH310	41	42	-0.01	3.1	0.4	2.35	-5	0.09
DODH310	42	43	-0.01	-0.5	-0.1	2.79	-5	0.01
DODH310	43	44	-0.01	-0.5	0.1	2.95	-5	0.01
DODH310	44	45	-0.01	-0.5	0.3	3.23	-5	0.01
DODH310	45	46	-0.01	-0.5	0.4	4.12	-5	0.02
DODH310	46	47	-0.01	-0.5	0.2	4.09	-5	0.01
DODH310	47	48	-0.01	-0.5	0.2	4.81	-5	0.02
DODH310	48	49	-0.01	-0.5	0.1	2.55	-5	0.01
DODH310	49	50	-0.01	-0.5	0.1	5.1	-5	0.02

Hole ID	Depth Fm	Depth To	Au (ppm)	Ag (ppm)	Te (ppm)	U (ppm)	Mo (ppm)	AuEq (g/t)
DODH314	0	1	0.37	19.8	8.1	12	-5	0.96
DODH314	1	2	0.21	13.6	4.2	4.17	-5	0.60
DODH314	2	3	0.05	18.9	4.3	2.61	-5	0.56
DODH314	3	4	0.06	17.8	12.7	3.26	-5	0.61
DODH314	4	5	0.04	9.3	3.7	2.91	-5	0.31
DODH314	5	6	0.06	19.5	7.9	3.86	-5	0.62
DODH314	6	7	0.06	20.4	2.7	2.85	-5	0.60
DODH314	7	8	0.01	26.8	0.7	3.79	-5	0.70
DODH314	8	9	0.02	19.4	2.1	4.46	5	0.54
DODH314	9	10	0.01	19.8	0.7	4.08	7	0.53
DODH314	10	11	0.01	16.7	0.7	3.69	7	0.45
DODH314	11	12	0.31	22.1	9.6	4.76	7	0.96
DODH314	12	13	0.03	14.5	1	5.41	9	0.43
DODH314	13	14	0.06	8.8	2.5	5.41	9	0.33
DODH314	14	15	0.68	4.2	0.9	6.12	7	0.82
DODH314	15	16	0.09	7.2	3.8	4.79	7	0.32
DODH314	16	17	0.07	5.6	3.1	5.34	10	0.26
DODH314	17	18	0.01	7.3	1	4.71	7	0.22
DODH314	18	19	0.02	9.1	1.9	4.11	7	0.28
DODH314	19	20	0.01	1.2	1.1	4.49	8	0.07
DODH314	20	21	0.02	6.3	0.8	5.89	20	0.23
DODH314	21	22	0.02	3.3	0.7	7.85	12	0.15
DODH314	22	23	0.02	4	1.1	8.41	9	0.17
DODH314	23	24	0.03	11	2.4	12	9	0.37
DODH314	24	25	-0.01	1.7	0.9	17.6	6	0.11
DODH314	25	26	0.08	5	3.5	34.2	164	0.57
DODH314	26	27	3.33	200	129	62.2	18500	35.95
DODH314	27	28	5.28	400	249	109	22600	49.83
DODH314	28	29	0.57	41.5	17.1	7.6	101	1.91
DODH314	29	30	0.11	24.4	8.9	6.01	48	0.88
DODH314	30	31	0.04	2.3	1.7	2.56	130	0.30
DODH314	31	32	-0.01	1.8	0.7	4.88	-5	0.07
DODH314	32	33	-0.01	-0.5	0.1	2.04	-5	0.01
DODH314	33	34	-0.01	1.1	0.4	2.84	-5	0.04
DODH314	34	35	-0.01	1	0.3	2.64	-5	0.04
DODH314	35	35.5	-0.01	2.5	0.8	2.9	-5	0.08