

2 May 2007

The Manager  
Company Announcements Office  
ASX Ltd  
4<sup>th</sup> Floor, 20 Bridge Street  
SYDNEY. NSW 2000

## **ROCKLANDS GROUP COPPER PROJECT (CDU 100%)**

### **High Grade Copper, Cobalt, Gold - Las Minerale and Central Rocklands**

The infill drilling program within the central 800m long supergene zone of the 1250m Las Minerale strike (The Central Zone) continues to produce strong results. Drilling in the SE of the Central Zone, east of the high grade supergene zone (native copper and chalcocite) appears to be increasing in width. Gold grades appear also to be increasing in the eastern Central Zone.

- Diamond Drill Hole LMDH 017 intersected a number of mineralized zones including 27m @ 7.71%Cu, 554ppm Co and 0.88g/t Au from 76-103m which included 14m @ 14.36%Cu, 919ppm Co and 1.35 g/t Au from 76-90m. Cobalt assay results exceeding 1000ppm extended outside the main Cu, Au intersection.
- RC Drill Hole LMRC 008 intersected high grade copper, cobalt and gold with 41m @ 2.09% Cu from 61-102m including 24m @ 2.59% Cu, 1038ppm Co and 0.71g/t Au from 62 to 86m and 15m @ 1.01g/t Au from 64-79m.
- RC Drill Hole LMRC 012 intersected 36m @ 1.34% Cu from 26 - 62m including 25m @ 2.41% Cu from 41 - 56m.
- Diamond Drill Hole LMDH 014 intersected 39m @ 1.85% Cu, 800ppm Co and 0.21g/t Au from 26 - 65m.
- RC Drill Hole LMRC 016 intersected 43m @ 2.00% Cu from 53-96m including 8m @ 4.94% Cu from 78-86m and 27m @ 2.88% Cu from 66-93m with high grade Cobalt (up to 1880ppm) and Gold (up to 1.82g/t) credits.

- RC Drill Hole LMRC 010 intersected 43m @ 0.80% Cu from 57-100m including 12m @ 1.52%Cu from 70-82m and with high Cobalt credits.
- RC Drill Hole LMRC 014 intersected 55m @ 0.79%Cu from 142-197m including 27m @ 1.23% Cu from 143-170m
- RC Drill Hole LMRC 007 Intersected 46m @ 4.94% Cu from 66-112m including 29m @ 7.46% Cu from 83-112m with exceptionally high gold, cobalt credits. For example, Gold assays returned 20m @ 4.59 g/t Au from 83-103m including 15m @ 5.98 g/t Au from 85 to 100m and 7m @ 11.38g/t Au from 86 to 93m (which included 1m @ 56.50 g/t Au from 90 to 91 m).
- RC Drill Hole LMDH 015 was a shallow hole into the oxide zone and intersected high Cu, Co, Au with 17m @ 2.09% Cu from 6-23m
- Diamond Drill Hole LMDH 012 (previously reported on 23 March 2007 for Cu only) intersected 37m @ 4.04% Cu, 663ppm Co and 0.83g/t Au from 111-148m including 11m @ 10.61% Cu, 779ppm Co and 0.63g/t Au. Very high grade intersections up to 26.50% Cu, 3080ppm Co (0.31%) and 8.29g/t Au were also returned.
- Latest drilling of the Central Rocklands Copper Project is delivering encouraging and expected results. Central Rocklands is approx 1km wide and appears to consist of five subordinate shears which previous drilling indicates possibly up to 5 parallel zones containing copper, cobalt and gold mineralization

Results from infill drilling to the East are returning high Cobalt, Gold grades coincident with high grade chalcocite (copper sulphide mineral) and, adding significant mineral credits to the high grade Las Minerale Central Zone particularly with current prices. For example, Cobalt prices have firmed from \$U15/lb to in excess of \$US25/lb (i.e. \$U55,000/). *The Credit Suisse Group recently forecast Cobalt may increase to circa \$US40/lb by end of 2007.*<sup>1</sup>

Furthermore, Gold has firmed to U\$685/ounce which is equivalent to U\$22/gram .

Directors at CuDeco Ltd advise Shareholders that the Rocklands Copper Project is progressing as expected with infill drilling providing more high grade copper, cobalt and gold grades. Drilling on the mid southern end of Las Minerale shows the width appearing to widen. Grades are remaining consistently high particularly in the 800m long supergene zone which is subject to the intense in fill drill program.

---

<sup>1</sup> "Cobalt Price Forecast Raised 67% by Credit Suisse as Use Surges", by Alistair Holloway, Bloomberg.com April 13, 2007.

## **Central Rocklands Drilling**

The Central Rocklands prospect is part of the principal mineralized "Rocklands Central" structure which is traceable over 2000m of strike and at least five subordinate shears within an area approx 1km wide inclusive of Las Minerale Southern Extension. The aggregated lengths of various structures within the main structure are estimated to be 6000m long and collectively present a significant resource target. The area abuts Las Minerale to the south east and the mineralization may be of the same genesis.

Drill Hole DORC 211 at Central Rocklands was follow up hole, designed to further test intersections defined in shallow oxide holes at the start of the Rocklands drilling programme in early 2006. Sulphides together with outcropping malachite had been observed in the vicinity of DORC 211.

Currently this zone is being tested on a 50m spacing along an 800m strike.

To date, Copper and Gold assay results are encouraging.

DORC 211, drilled 25m behind DORC 006 (an earlier drill hole with high grade Cu intercepts), intersected 29m of continuous mineralization from 67 - 96m containing 1.38% Cu, 289ppm Co and 0.67 g/t Au, including 20m @ 1.83% Cu, 289ppm Co and 0.67g/t Au from 75 - 95m including 12m @ 2.40% Cu, 429ppm Co and 1.18g/t Au from 75-87m confirming the continuation of mineralization below Drill Hole DORC 006.

A further ten exploration holes have since been drilled along strike with visual copper oxide (malachite) and sulphides (chalcopyrite) and a further 6 sites have been prepared for drilling.

Yours faithfully



Wayne McCrae  
Chairman

*The information in this report that relates to exploration results is based on information compiled by Mr Malcolm Carson , who is a Member of the Australian Institute of Mining and Metallurgy, Mr Carson is employed by Mineral Resource Consultants Pty Ltd. Mr Carson has sufficient experience, which is relevant to the style of mineralisation and type of deposit under consideration and to the activity which he is undertaking to qualify as a Competent Person as defined in the 2004 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'. Mr Carson consents to the inclusion in this report of the matters based on his information in the form and context in which it appears.*



TV061748	97	24	Co	Cu	Au
61775 / LMDH 017	270307		AAS22D	AAS22D	FAA505
METHOD			10	0.01	0.01
LDETECTION			50000	50.00	1,000.00
UDETECTION			PPM	%	PPM
UNITS					
LMDH 017 / 031-032			250	0.24	0.02
LMDH 017 / 032-033			230	0.28	0.03
LMDH 017 / 033-034			310	0.17	-
LMDH 017 / 034-035			310	0.15	-
LMDH 017 / 035-036			280	0.05	-
LMDH 017 / 036-037			240	0.08	-
LMDH 017 / 037-038			240	0.13	-
LMDH 017 / 038-039			300	0.06	-
LMDH 017 / 039-040			300	0.08	-
LMDH 017 / 040-041			600	0.08	-
LMDH 017 / 041-042			510	0.25	0.05
LMDH 017 / 042-043			460	0.16	-
LMDH 017 / 043-044			410	0.11	-
LMDH 017 / 044-045			550	0.16	-
LMDH 017 / 045-046			620	0.24	X
LMDH 017 / 046-047			830	0.13	-
LMDH 017 / 047-048			1350	0.21	0.02
LMDH 017 / 048-049			1300	0.15	-
LMDH 017 / 049-050			540	0.19	-
LMDH 017 / 050-051			1350	0.19	-
LMDH 017 / 051-052			920	0.20	-
LMDH 017 / 052-053			790	0.55	0.08
LMDH 017 / 053-054			790	0.22	0.30
LMDH 017 / 054-055			650	0.17	-
LMDH 017 / 055-056			620	0.16	-
LMDH 017 / 056-057			440	0.12	-
LMDH 017 / 057-058			290	0.05	-
LMDH 017 / 058-059			450	0.03	-
LMDH 017 / 059-060			430	0.11	-
LMDH 017 / 060-061			470	0.03	-
LMDH 017 / 061-062			570	0.02	-
LMDH 017 / 062-063			1040	0.04	-
LMDH 017 / 063-064			810	0.18	-
LMDH 017 / 064-065			1270	0.13	-
LMDH 017 / 065-066			1500	0.05	-
LMDH 017 / 066-067			770	0.09	-
LMDH 017 / 067-068			1450	0.41	0.02
LMDH 017 / 068-069			1180	0.22	X
LMDH 017 / 069-070			1140	0.04	-
LMDH 017 / 070-071			1440	0.05	-
LMDH 017 / 071-072			960	0.13	-
LMDH 017 / 072-073			1300	0.14	-
LMDH 017 / 073-074			920	0.04	-
LMDH 017 / 074-075			1170	0.07	-
LMDH 017 / 075-076			850	0.10	-
LMDH 017 / 076-077			630	7.43	0.31
LMDH 017 / 077-078			740	22.20	0.65
LMDH 017 / 078-079			850	14.00	1.80
LMDH 017 / 079-080			1040	13.20	4.99

TV061748	97	24	Co	Cu	Au
61775 / LMDH 017	270307		AAS22D	AAS22D	FAA505
METHOD					
LDETECTION			10	0.01	0.01
UDETECTION			50000	50.00	1,000.00
UNITS			PPM	%	PPM
LMDH 017 / 080-081			830	20.30	2.65
LMDH 017 / 081-082			1090	13.70	1.33
LMDH 017 / 082-083			920	14.50	2.56
LMDH 017 / 083-084			690	23.80	1.45
LMDH 017 / 084-085			1270	18.80	0.73
LMDH 017 / 085-086			1390	6.50	0.44
LMDH 017 / 086-087			1330	6.85	0.70
LMDH 017 / 087-088			940	16.30	0.50
LMDH 017 / 088-089			610	5.13	0.42
LMDH 017 / 089-090			540	18.30	0.30
LMDH 017 / 090-091			750	0.76	0.23
LMDH 017 / 091-092			280	0.69	0.11
LMDH 017 / 092-093			270	0.44	0.04
LMDH 017 / 093-094			180	0.27	0.01
LMDH 017 / 094-095			110	0.36	0.02
LMDH 017 / 095-096			90	0.40	X
LMDH 017 / 096-097			100	0.49	0.01
LMDH 017 / 097-098			90	0.45	X
LMDH 017 / 098-099			50	0.26	0.01
LMDH 017 / 099-100			40	0.11	-
LMDH 017 / 100-101			40	1.48	X
LMDH 017 / 101-102			30	0.02	-
LMDH 017 / 102-103			50	1.39	0.01

TV061749 124 24  
61775 / LMRC 008 270307

## METHOD

LDETECTION

UDETECTION

UNITS

	Co AAS22D 10 50000 PPM	Cu AAS22D 0.01 50.00 %	Cu(R) AAS22D 0.01 30.00 %	Au FAA505 0.01 1,000.00 PPM
LMRC 008 / 062	380	2.61	-	0.13
LMRC 008 / 063	360	6.86	6.60	0.12
LMRC 008 / 064	1100	1.68	-	0.14
LMRC 008 / 065	850	2.91	4.01	0.51
LMRC 008 / 066	910	1.02	-	2.86
LMRC 008 / 067	650	10.50	13.00	0.77
LMRC 008 / 068	810	1.67	-	0.19
LMRC 008 / 069	980	0.61	-	0.42
LMRC 008 / 070	1100	0.82	-	2.85
LMRC 008 / 071	1670	0.41	-	2.95
LMRC 008 / 072	1170	3.01	-	1.54
LMRC 008 / 073	920	1.91	-	0.34
LMRC 008 / 074	1210	2.87	-	0.45
LMRC 008 / 075	1260	3.04	-	0.66
LMRC 008 / 076	1110	3.72	3.19	0.54
LMRC 008 / 077	840	3.83	-	0.63
LMRC 008 / 078	1440	0.61	-	0.14
LMRC 008 / 079	1420	1.58	-	0.31
LMRC 008 / 080	880	1.22	-	0.07
LMRC 008 / 081	1440	0.53	-	0.03
LMRC 008 / 082	1180	0.75	-	0.08
LMRC 008 / 083	1300	0.53	-	X
LMRC 008 / 084	1230	2.86	-	0.35
LMRC 008 / 085	780	7.11	8.00	0.89
LMRC 008 / 086	950	2.06	-	0.12
LMRC 008 / 087	860	0.93	-	0.04
LMRC 008 / 088	1110	0.89	-	0.03
LMRC 008 / 089	870	1.07	-	0.04
LMRC 008 / 090	760	1.96	-	0.02
LMRC 008 / 091	900	1.95	-	0.02
LMRC 008 / 092	770	0.80	0.83	0.02
LMRC 008 / 093	740	0.95	-	0.05
LMRC 008 / 094	850	1.41	-	0.13
LMRC 008 / 095	970	0.73	-	0.05
LMRC 008 / 096	1020	1.10	-	0.06
LMRC 008 / 097	920	1.15	-	0.06
LMRC 008 / 098	1030	1.88	-	0.35
LMRC 008 / 099	1020	1.86	-	0.21
LMRC 008 / 100	360	0.28	-	0.04
LMRC 008 / 101	220	2.84	-	0.04
LMRC 008 / 102	200	1.27	-	0.03

TV061739	82	16	Co	Cu	Au
61780 / LMRC 012	270307		AAS22D	AAS22D	FAA505
METHOD			10	0.01	0.01
LDETECTION			50000	50.00	1,000.00
UDETECTION			PPM	%	PPM
UNITS					
LMRC 012 / 26			260	0.67	0.12
LMRC 012 / 27			430	3.24	0.15
LMRC 012 / 28			520	0.12	-
LMRC 012 / 29			280	0.08	-
LMRC 012 / 30			400	0.53	0.02
LMRC 012 / 31			650	0.07	-
LMRC 012 / 32			510	0.07	-
LMRC 012 / 33			620	0.07	-
LMRC 012 / 34			690	0.09	-
LMRC 012 / 35			530	0.11	-
LMRC 012 / 36			520	0.12	-
LMRC 012 / 37			630	0.27	0.40
LMRC 012 / 38			740	1.12	0.16
LMRC 012 / 39			760	0.42	0.13
LMRC 012 / 40			610	0.76	0.08
LMRC 012 / 41			550	0.23	0.10
LMRC 012 / 42			650	1.69	0.27
LMRC 012 / 43			1660	1.56	0.19
LMRC 012 / 44			1650	1.26	0.44
LMRC 012 / 45			1620	2.39	0.34
LMRC 012 / 46			2320	5.39	0.39
LMRC 012 / 47			1100	3.10	0.29
LMRC 012 / 48			650	1.41	0.17
LMRC 012 / 49			580	2.26	0.34
LMRC 012 / 50			410	1.56	0.20
LMRC 012 / 51			1080	6.26	0.77
LMRC 012 / 52			1410	1.47	0.17
LMRC 012 / 53			1300	2.21	0.47
LMRC 012 / 54			780	2.00	0.22
LMRC 012 / 55			650	1.17	0.09
LMRC 012 / 56			730	2.37	0.29
LMRC 012 / 57			400	0.63	0.09
LMRC 012 / 58			210	0.23	0.04
LMRC 012 / 59			400	0.49	0.09
LMRC 012 / 60			420	1.50	0.27
LMRC 012 / 61			390	1.46	0.29
LMRC 012 / 62			250	1.08	0.11

TV061677	59	16		
61764 / JOB 2	20030	Co	Cu	Au
METHOD		AAS22D	AAS22D	FAA505
LDETECTION		10	0.01	0.01
UDETECTION		50000	50.00	1,000.00
UNITS		PPM	%	PPM
LMDH 014 / 26-27		980	0.67	0.03
LMDH 014 / 27-28		520	2.87	0.03
LMDH 014 / 28-29		760	1.54	0.03
LMDH 014 / 29-30		1450	14.30	0.07
LMDH 014 / 30-31		1090	0.11	-
LMDH 014 / 31-32		680	0.11	-
LMDH 014 / 32-33		980	0.65	0.10
LMDH 014 / 33-34		1130	0.35	-
LMDH 014 / 34-35		1490	0.52	0.03
LMDH 014 / 35-36		970	1.39	0.03
LMDH 014 / 36-37		1110	0.54	X
LMDH 014 / 37-38		910	0.27	-
LMDH 014 / 38-39		1430	0.50	0.03
LMDH 014 / 39-40		1080	3.62	0.53
LMDH 014 / 40-41		1010	2.62	0.30
LMDH 014 / 41-42		1100	1.20	0.10
LMDH 014 / 42-43		920	0.56	0.10
LMDH 014 / 43-44		1050	0.39	-
LMDH 014 / 44-45		1010	0.24	0.17
LMDH 014 / 45-46		980	3.49	-
LMDH 014 / 46-47		1070	0.12	-
LMDH 014 / 47-48		1200	0.14	-
LMDH 014 / 48-49		690	0.18	-
LMDH 014 / 49-50		680	0.09	-
LMDH 014 / 50-51		510	0.36	-
LMDH 014 / 51-52		50	2.65	0.20
LMDH 014 / 52-53		690	0.34	-
LMDH 014 / 53-54		200	8.00	0.70
LMDH 014 / 54-55		610	0.61	0.53
LMDH 014 / 55-56		580	0.24	-
LMDH 014 / 56-57		630	0.50	0.07
LMDH 014 / 57-58		350	4.57	0.07
LMDH 014 / 58-59		360	1.97	0.43
LMDH 014 / 59-60		370	2.00	0.57
LMDH 014 / 60-61		620	2.69	0.10
LMDH 014 / 61-62		680	1.63	-
LMDH 014 / 62-63		380	0.59	-
LMDH 014 / 63-64		580	0.95	0.10
LMDH 014 / 64-65		290	8.64	0.60

TV061891 110 24  
61787 / LMRC016 - JO130407

	Co	Cu	Au
METHOD	AAS22D	AAS22D	FAA505
LDETECTION	10	0.01	0.01
UDETECTION	50000	50.00	1,000.00
UNITS	PPM	%	PPM
LMRC016 / 054	250	0.70	0.13
LMRC016 / 055	600	0.92	0.19
LMRC016 / 056	580	0.75	0.14
LMRC016 / 057	390	0.26	0.04
LMRC016 / 058	500	0.32	0.05
LMRC016 / 059	1080	0.51	0.09
LMRC016 / 060	1000	0.35	0.05
LMRC016 / 061	1000	0.61	0.16
LMRC016 / 062	1460	0.89	0.21
LMRC016 / 063	1040	0.35	0.07
LMRC016 / 064	720	0.27	0.02
LMRC016 / 065	460	0.15	-
LMRC016 / 066	470	0.99	0.15
LMRC016 / 067	850	2.43	0.28
LMRC016 / 068	1520	0.70	0.06
LMRC016 / 069	1460	1.42	0.16
LMRC016 / 070	920	2.51	0.32
LMRC016 / 071	570	1.56	0.12
LMRC016 / 072	130	0.31	0.11
LMRC016 / 073	920	2.08	0.20
LMRC016 / 074	1060	1.74	0.18
LMRC016 / 075	1440	2.15	0.28
LMRC016 / 076	1650	1.74	0.24
LMRC016 / 077	870	1.51	0.14
LMRC016 / 078	1880	8.19	0.94
LMRC016 / 079	1410	7.66	1.06
LMRC016 / 080	1930	9.71	1.82
LMRC016 / 081	600	2.03	0.28
LMRC016 / 082	900	2.03	0.22
LMRC016 / 083	1090	2.05	0.30
LMRC016 / 084	1410	4.50	0.62
LMRC016 / 085	1070	5.35	4.90
LMRC016 / 086	810	2.98	0.86
LMRC016 / 087	190	0.70	0.06
LMRC016 / 088	470	0.73	0.76
LMRC016 / 089	1140	1.63	0.22
LMRC016 / 090	1210	3.26	0.76
LMRC016 / 091	1430	3.50	0.28
LMRC016 / 092	970	3.78	0.38
LMRC016 / 093	1140	1.61	0.16
LMRC016 / 094	470	0.71	0.12
LMRC016 / 095	170	0.22	X
LMRC016 / 096	210	0.28	0.06

TV061740	119	16	Co	Cu	Au
61781 / LMRC 010	270307		AAS22D	AAS22D	FAA505
METHOD					
LDETECTION			10	0.01	0.01
UDETECTION			50000	50.00	1,000.00
UNITS			PPM	%	PPM
LMRC 010 / 058			810	0.24	0.02
LMRC 010 / 059			680	0.24	0.04
LMRC 010 / 060			1050	0.23	0.01
LMRC 010 / 061			560	0.10	-
LMRC 010 / 062			160	0.08	-
LMRC 010 / 063			80	0.06	-
LMRC 010 / 064			210	0.04	-
LMRC 010 / 065			140	0.81	0.09
LMRC 010 / 066			100	0.40	0.07
LMRC 010 / 067			350	0.77	0.12
LMRC 010 / 068			240	0.43	0.08
LMRC 010 / 069			540	0.36	0.06
LMRC 010 / 070			820	0.32	0.05
LMRC 010 / 071			980	2.28	0.20
LMRC 010 / 072			610	1.48	0.15
LMRC 010 / 073			470	1.13	0.16
LMRC 010 / 074			1090	2.00	0.22
LMRC 010 / 075			470	1.50	0.18
LMRC 010 / 076			340	1.34	0.17
LMRC 010 / 077			1410	1.27	0.20
LMRC 010 / 078			590	0.44	0.07
LMRC 010 / 079			950	1.95	0.22
LMRC 010 / 080			780	1.45	0.16
LMRC 010 / 081			830	2.02	0.22
LMRC 010 / 082			570	1.39	0.13
LMRC 010 / 083			970	0.87	0.10
LMRC 010 / 084			490	0.73	0.08
LMRC 010 / 085			500	1.20	0.17
LMRC 010 / 086			980	0.67	0.08
LMRC 010 / 087			920	0.83	0.13
LMRC 010 / 088			930	0.35	0.06
LMRC 010 / 089			1330	0.45	0.04
LMRC 010 / 090			1480	0.69	0.03
LMRC 010 / 091			1110	0.56	0.04
LMRC 010 / 092			1200	0.71	0.07
LMRC 010 / 093			890	1.32	0.12
LMRC 010 / 094			550	0.21	0.02
LMRC 010 / 095			880	1.03	0.10
LMRC 010 / 096			920	1.89	0.24
LMRC 010 / 097			180	0.22	0.03
LMRC 010 / 098			90	0.07	-
LMRC 010 / 099			130	0.17	-
LMRC 010 / 100			50	0.29	0.03

TV061795	221	24	Co	Cu	Au
61782 / LMRC 014	300307		AAS22D	AAS22D	FAA505
METHOD					
LDETECTION			10	0.01	0.01
UDETECTION			50000	50.00	1,000.00
UNITS			PPM	%	PPM
LMRC 014 / 143			80	0.31	0.12
LMRC 014 / 144			130	1.64	0.53
LMRC 014 / 145			760	2.51	0.33
LMRC 014 / 146			610	2.41	0.47
LMRC 014 / 147			880	1.82	0.50
LMRC 014 / 148			710	1.42	0.32
LMRC 014 / 149			620	2.09	0.33
LMRC 014 / 150			860	1.58	0.31
LMRC 014 / 151			1010	1.34	0.21
LMRC 014 / 152			600	1.39	0.20
LMRC 014 / 153			350	0.96	0.12
LMRC 014 / 154			320	1.20	0.18
LMRC 014 / 155			490	1.84	0.30
LMRC 014 / 156			370	0.80	0.09
LMRC 014 / 157			310	0.37	0.02
LMRC 014 / 158			340	0.75	0.10
LMRC 014 / 159			440	0.81	0.07
LMRC 014 / 160			360	0.42	0.07
LMRC 014 / 161			300	0.29	0.06
LMRC 014 / 162			380	0.44	0.05
LMRC 014 / 163			280	0.41	0.04
LMRC 014 / 164			270	0.84	0.08
LMRC 014 / 165			230	0.99	0.12
LMRC 014 / 166			250	1.94	2.19
LMRC 014 / 167			220	1.43	0.74
LMRC 014 / 168			320	1.57	0.57
LMRC 014 / 169			130	0.57	0.09
LMRC 014 / 170			160	2.16	0.23
LMRC 014 / 171			90	0.73	0.06
LMRC 014 / 172			80	0.28	0.04
LMRC 014 / 173			60	0.26	0.04
LMRC 014 / 174			40	0.13	0.03
LMRC 014 / 175			50	0.37	0.07
LMRC 014 / 176			30	0.06	-
LMRC 014 / 177			50	0.14	-
LMRC 014 / 178			50	0.14	-
LMRC 014 / 179			70	0.23	0.07
LMRC 014 / 180			40	0.08	-
LMRC 014 / 181			40	0.02	-
LMRC 014 / 182			40	0.04	-
LMRC 014 / 183			40	0.08	-
LMRC 014 / 184			40	0.13	-
LMRC 014 / 185			70	0.14	-
LMRC 014 / 186			90	0.48	0.07
LMRC 014 / 187			70	0.36	0.04
LMRC 014 / 188			100	0.27	0.04
LMRC 014 / 189			90	0.41	0.07
LMRC 014 / 190			80	0.20	-
LMRC 014 / 191			110	0.36	0.06

TV061795	221	24			
61782 / LMRC 014	300307		Co	Cu	Au
METHOD			AAS22D	AAS22D	FAA505
LDETECTION			10	0.01	0.01
UDETECTION			50000	50.00	1,000.00
UNITS			PPM	%	PPM
LMRC 014 / 192			110	0.49	0.10
LMRC 014 / 193			200	0.45	0.06
LMRC 014 / 194			380	0.34	0.06
LMRC 014 / 195			820	1.14	0.43
LMRC 014 / 196			780	1.08	0.17
LMRC 014 / 197			410	0.58	0.07

TV061684 166	16		
61768 / LMRC 007	2	Co	Cu Au
METHOD		AAS22D	AAS22D FAA505
LDETECTION	10	0.01	0.01
UDETECTION	50000	50.00	1,000.00
UNITS	PPM	%	PPM
LMRC 007 / 058	250	0.31	0.03
LMRC 007 / 059	360	0.24	0.01
LMRC 007 / 060	310	0.19	-
LMRC 007 / 061	230	0.13	-
LMRC 007 / 062	180	0.11	-
LMRC 007 / 063	190	0.09	-
LMRC 007 / 064	220	0.04	-
LMRC 007 / 065	250	0.08	-
LMRC 007 / 066	270	0.19	0.03
LMRC 007 / 067	240	0.36	0.01
LMRC 007 / 068	330	0.24	0.03
LMRC 007 / 069	420	0.21	0.01
LMRC 007 / 070	580	0.11	-
LMRC 007 / 071	620	0.38	0.01
LMRC 007 / 072	570	0.16	-
LMRC 007 / 073	700	0.24	0.10
LMRC 007 / 074	720	0.27	0.36
LMRC 007 / 075	620	0.20	0.02
LMRC 007 / 076	480	0.18	-
LMRC 007 / 077	440	0.24	0.03
LMRC 007 / 078	550	0.10	-
LMRC 007 / 079	530	0.07	-
LMRC 007 / 080	640	0.27	0.01
LMRC 007 / 081	810	0.27	0.01
LMRC 007 / 082	870	0.14	-
LMRC 007 / 083	610	0.24	0.11
LMRC 007 / 084	870	6.80	0.35
LMRC 007 / 085	700	12.80	0.53
LMRC 007 / 086	620	14.90	1.03
LMRC 007 / 087	690	19.00	2.39
LMRC 007 / 088	970	25.80	3.46
LMRC 007 / 089	800	12.20	12.70
LMRC 007 / 090	930	13.30	0.83
LMRC 007 / 091	1230	12.50	56.50
LMRC 007 / 092	1110	7.48	1.76
LMRC 007 / 093	990	10.60	2.03
LMRC 007 / 094	1190	12.60	1.73
LMRC 007 / 095	1700	9.02	1.30
LMRC 007 / 096	1470	7.18	1.18
LMRC 007 / 097	1580	7.79	1.63
LMRC 007 / 098	1380	10.60	1.10
LMRC 007 / 099	850	16.80	1.03
LMRC 007 / 100	1210	11.40	1.03
LMRC 007 / 101	650	6.99	0.71
LMRC 007 / 102	1110	1.47	0.32
LMRC 007 / 103	450	0.79	0.28
LMRC 007 / 104	230	1.32	0.15
LMRC 007 / 105	200	0.23	0.12
LMRC 007 / 106	80	0.18	-

TV061684 166	16			
61768 / LMRC 007	2	Co	Cu	Au
METHOD		AAS22D	AAS22D	FAA505
LDETECTION		10	0.01	0.01
UDETECTION		50000	50.00	1,000.00
UNITS		PPM	%	PPM
LMRC 007 / 107		90	0.25	0.07
LMRC 007 / 108		90	0.13	-
LMRC 007 / 109		90	0.16	-
LMRC 007 / 110		110	0.23	0.07
LMRC 007 / 111		110	0.17	-
LMRC 007 / 112		310	0.86	0.30
LMRC 007 / 113		70	0.15	-
LMRC 007 / 114		70	0.11	-
LMRC 007 / 115		60	0.14	-
LMRC 007 / 116		70	0.13	-
LMRC 007 / 117		40	0.06	-
LMRC 007 / 118		80	0.24	0.05

TV061747	30	24	Co	Cu	Cu(R)	Au
61775 / LMDH 015	270307		AAS22D	AAS22D	AAS22D	FAA505
METHOD			10	0.01	0.01	0.01
LDETECTION			50000	50.00	30.00	1,000.00
UDETECTION			PPM	%	%	PPM
UNITS						
LMDH 015 / 06-07			540	0.23	-	-
LMDH 015 / 07-08			1070	0.36	-	0.03
LMDH 015 / 08-09			1270	0.37	-	0.04
LMDH 015 / 09-10			270	0.63	0.63	0.02
LMDH 015 / 10-11			1010	0.44	-	0.04
LMDH 015 / 11-12			890	0.35	-	0.14
LMDH 015 / 12-13			1170	0.38	-	0.10
LMDH 015 / 13-14			980	0.66	-	0.06
LMDH 015 / 14-15			1050	0.76	-	0.13
LMDH 015 / 15-16			850	0.68	-	0.40
LMDH 015 / 16-17			1150	0.82	-	0.45
LMDH 015 / 17-18			1180	1.26	-	0.40
LMDH 015 / 18-19			690	8.67	-	0.52
LMDH 015 / 19-20			630	9.53	-	0.38
LMDH 015 / 20-21			430	4.64	-	0.29
LMDH 015 / 21-22			450	5.57	-	0.62
LMDH 015 / 22-23			300	0.22	-	0.02

TV061616 63 16	Co	Cu	Au
61756 / LMDH012 - JO090307	AAS22D	AAS22D	FAA505
METHOD	10	0.01	0.01
LDETECTION	50000	50.00	1,000.00
UDETECTION			
UNITS	PPM	%	PPM
LMDH 012 111-112	230	1.01	0.17
LMDH 012 112-113	560	0.28	-
LMDH 012 113-114	630	0.30	-
LMDH 012 114-115	400	0.18	-
LMDH 012 115-116	990	1.98	0.07
LMDH 012 116-117	1090	0.34	-
LMDH 012 117-118	1210	0.37	-
LMDH 012 118-119	1260	1.09	0.17
LMDH 012 119-120	1700	0.32	-
LMDH 012 120-121	1610	0.11	-
LMDH 012 121-122	1030	1.11	0.47
LMDH 012 122-123	290	0.32	-
LMDH 012 123-124	240	0.36	-
LMDH 012 124-125	360	1.36	0.07
LMDH 012 125-126	40	0.08	-
LMDH 012 126-127	70	0.25	-
LMDH 012 127-128	450	3.78	0.30
LMDH 012 128-129	440	3.81	0.70
LMDH 012 129-130	440	5.82	0.70
LMDH 012 130-131	830	0.36	-
LMDH 012 131-132	680	0.43	-
LMDH 012 132-133	500	5.01	8.29
LMDH 012 133-134	590	2.35	0.30
LMDH 012 134-135	210	0.47	-
LMDH 012 135-136	410	1.09	0.10
LMDH 012 136-137	260	2.43	0.20
LMDH 012 137-138	390	9.70	0.70
LMDH 012 138-139	540	9.70	2.35
LMDH 012 139-140	3090	5.87	1.05
LMDH 012 140-141	940	3.77	0.30
LMDH 012 141-142	1330	2.26	0.27
LMDH 012 142-143	1040	7.50	0.53
LMDH 012 143-144	120	25.90	0.37
LMDH 012 144-145	200	26.50	0.70
LMDH 012 145-146	250	22.00	0.40
LMDH 012 146-147	60	0.81	0.07
LMDH 012 147-148	60	0.38	-

TV061745 161 24  
61173 / DORC 211 270307

METHOD	Co AAS22D	Cu AAS22D	Cu(R) AAS22D	Au FAA505
LDETECTION	10	0.01	0.01	0.01
UDETECTION	50000	50.00	30.00	1,000.00
UNITS	PPM	%	%	PPM
DORC 211 / 058	50	0.55	-	0.11
DORC 211 / 059	140	0.73	-	0.18
DORC 211 / 060	70	0.25	-	0.01
DORC 211 / 061	10	0.05	-	-
DORC 211 / 062	20	X	-	-
DORC 211 / 063	X	0.03	-	-
DORC 211 / 064	X	X	-	-
DORC 211 / 065	X	X	-	-
DORC 211 / 066	130	0.02	-	-
DORC 211 / 067	170	0.11	-	-
DORC 211 / 068	220	0.30	-	0.14
DORC 211 / 069	30	X	-	-
DORC 211 / 070	20	0.03	-	-
DORC 211 / 071	20	0.02	-	-
DORC 211 / 072	80	0.64	-	0.03
DORC 211 / 073	70	0.18	-	-
DORC 211 / 074	50	0.06	-	-
DORC 211 / 075	410	0.60	-	0.76
DORC 211 / 076	330	2.37	-	3.99
DORC 211 / 077	80	0.11	-	-
DORC 211 / 078	790	8.17	-	4.33
DORC 211 / 079	610	8.21	-	2.40
DORC 211 / 080	1870	1.29	-	0.37
DORC 211 / 081	120	1.60	-	0.78
DORC 211 / 082	160	0.48	-	0.08
DORC 211 / 083	210	1.58	-	0.46
DORC 211 / 084	180	0.46	0.44	0.21
DORC 211 / 085	170	0.41	-	0.05
DORC 211 / 086	200	1.55	-	0.12
DORC 211 / 087	430	2.62	-	0.19
DORC 211 / 088	180	0.32	-	0.08
DORC 211 / 089	410	1.70	-	0.23
DORC 211 / 090	150	0.53	-	0.06
DORC 211 / 091	250	0.39	-	0.09
DORC 211 / 092	150	0.70	-	0.07
DORC 211 / 093	250	1.30	-	0.38
DORC 211 / 094	230	0.67	-	0.18
DORC 211 / 095	560	2.04	-	0.32
DORC 211 / 096	160	0.34	-	0.05
DORC 211 / 097	110	0.18	-	-
DORC 211 / 098	80	0.15	0.14	-
DORC 211 / 099	80	0.09	-	-
DORC 211 / 100	30	0.04	-	-
DORC 211 / 101	20	0.02	-	-
DORC 211 / 102	20	0.03	-	-
DORC 211 / 103	110	0.90	-	0.07
DORC 211 / 104	30	0.09	-	-
DORC 211 / 105	20	0.22	-	0.03
DORC 211 / 106	640	0.39	-	0.03
DORC 211 / 107	150	0.18	-	-

TV061745	161	24				
61173 / DORC 211	270307		Co	Cu	Cu(R)	Au
METHOD			AAS22D	AAS22D	AAS22D	FAA505
LDETECTION			10	0.01	0.01	0.01
UDETECTION			50000	50.00	30.00	1,000.00
UNITS			PPM	%	%	PPM
DORC 211 / 108			50	0.05	-	-
DORC 211 / 109			50	0.05	-	-
DORC 211 / 110			40	0.02	-	-
DORC 211 / 111			30	0.03	-	-
DORC 211 / 112			30	0.05	-	-
DORC 211 / 113			40	0.82	-	0.11